



Grout Mix is a pre-blended powder mixture of premium grade high quality sodium carbonate activated Bentonite powder and Ordinary Portland Cement (CEM 1) in a ratio of 2:1.

Applications

- Landfill gas wells
- Borehole sealing
- Grouting
- Isolating instrumentation and sampling zones

Packaging

- 25kg paper bags
- 40 bags per pallet

Features

- Easy to mix and use
- Consistent mix quality
- Stable suspension
- Rapid build up of viscosity
- Can be used with traditional mixing equipment
- Suitable for immediate use after mixing
- Cement to BS EN 197-1 CEM 1

Specifications		
	Bentonite	Cement
Colour	Light yellowish grey	Light grey
Odour	None	
pH	8.5-10	12-14
Specific Gravity	800 to 1100kg/m ³	1400kg/m ³
Moisture Content	12%	<5%
% by weight passing BS410 150 micron sieve	Min 95%	Min 95%

Mixes				
Litres/Water per Bag	30	35	40	50
Waters/ Solids Ratio	1.2	1.4	1.6	2
Wet Density kg/m ³	1340	1323	1315	1211
Yield per Bag	32.8 litres	41.1 litres	50 litres	70.6 litres